

Verzamel varkensneus ferriet info en metingen

Test met dun teflon en N = 5

micro Henry waarde, Q en AL

Ui

via shape factor

Breedte A=	hoogte B=	dikte C=	gat / hole H=	1 kHz	10kHz	100kHz	gemmid. AL	geschat Ui	bijzonderheden
13,5	13,8	7,8	4,1	17,8 3,4 712	17,7 30 708	17,7 120 708	710	285	via Barend H. met oranje verf
14,1	13,8	8,1	4,0	24 6,85 960	23,8 43 952	23,6 62 944	950	380	
14,6	13,5	8,4	4,1	1,2 0,2 48	1,2 1,96 48	1,2 18,8 48	+ / - 50	20	met witte verf
13,8	7,8	8,1	3,9	13,9 0,4 556	13,6 40 544	13,6 92 544	+/- 545	360	via BaCo een halve hoogte
30	14,7	14,8	5,5	31,9 2,11 319	31,8 20 318	31,8 100 318	318	+/- 60	N=10, geen 5 grote neus
14	13,8	8,1	3,8	2,7 0,48 108	2,75 4,75 110	2,72 44 109	110	+/- 44	gele verf
13,2	14,2	7,3	4,0	49,5 12 1980	49 49 1960	48,5 63 1940	+/- 2000	800	VK10 "43"?
13,9	8	8,2	3,8	12,7 4,6 508	12,68 37 507	12,55 99 502	505	335	VK11 halve hoogte
6,7	5,7	4	2	9,3 2 372	9,3 20 372	9,3 110 372	372	?	mini blokje
6,7	5,5	4,1	2	0,4 0,15 16	0,43 1,5 17	0,42 11 17	17	?	mini Veron? met iets groen
13,5	13,8	7,4	4	54 6,4 2160	46,8 5,6 1872	34,8 5,8 1392	+ / -2000	800	deze via ALI JETTING bruikbaar als "43"

