


Rosmalen 18-03-06

RINGKERN/FERRIET INFOBLAD

No.

Fabrikant	Meetmethode			AL in mH/1000	BJ2				Serie - R
	N	C pF	f _{res}		f ₁	f ₂	+R	LC	
Magnetics									
Type / kleur	10 A	1030	248	3998	243,5	253,3	25,3	30	} R = 100k →
ZF-42212-TC	10 B	1030	249,8	3941	245,6	254			
grijs coating	10 C	1030	247	4031	242	252,25			
Maten in mm									
Buiten \varnothing 22,7	1025 C	10000	81,21	3840	80,04	82,66	31	79	R = 10k →
Binnen \varnothing 13,3	1025 C	10000	81,30	3832	81,00	81,64	127	169	R = 100k →
Hoogte \blacksquare I \pm 13									
Kernmateriaal type F	Bijzonderheden								
R ₁	 <p>ZF-42212-TC \rightarrow Toroid core \pm 12 mm hoog \pm 22 mm \varnothing materiaal type F grijze coating</p>								
μ_{tot} / μ_1	\pm 3000 \pm 20% !!								
	Fabrikant AL = 3624 \pm 20% !!								